

## Hybrid polyelectrolyte/bacterial protein (nano)biomimetic surfaces: a model to study bacterial surface layer recovery and bacterial affinity

*Mihaela Delcea*<sup>1</sup>, *Dietmar Pum*<sup>2</sup>, *Rumen Krastev*<sup>3</sup>, *Uwe B. Sleytr*<sup>2</sup>  
and *José Luis Toca-Herrera*<sup>1</sup>

<sup>1</sup>Biosurfaces Unit, CICbiomaGUNE, Paseo Miramón 182, Parque Tecnológico de San Sebastián, 20009 San Sebastián (Gipuzkoa), Spain

<sup>2</sup>Center for Nanobiotechnology, BOKU, Gregor-Mendel Str. 33, 1180 Vienna, Austria

<sup>3</sup>Max-Planck Institute for Colloids and Interfaces, Am Muehlenberg 1, 14420 Potsdam, Germany

[mdelcea@cicbiomagune.es](mailto:mdelcea@cicbiomagune.es); [jltocaherrera@cicbiomagune.es](mailto:jltocaherrera@cicbiomagune.es)

Robust (nano)biomimetic surfaces that mimic the behaviour of cell membranes can be built by combining polyelectrolyte multilayer (PEM) deposition and bacterial surface layer technology [1]. This symbiosis can provide a variety of model systems and applications such as, artificial cells and biosensor development.

Polyelectrolytes are used as a cushion for crystalline bacterial cell surface layers (S-layers), replacing the secondary cell wall polymer from bacteria. S-layers are one of the most common cell envelope components of prokaryotic organisms, composed of a single (glyco)protein, representing the simplest biological membrane developed during evolution [2]. Isolated S-layer subunits have the ability to self-assemble into 2-D crystalline structures at the air-water interface [3], on lipid films [4], on liposomes [5], on solid support [6], on solid supports coated with polyelectrolytes and on hollow polyelectrolyte microcapsules [1]. The study of the stability of S-layers is relevant in microbiology and nanotechnology since they play among others, a protective role and can serve as a (nano)matrix for bio-immobilization.

Our studies show that recrystallized S-layers (from *Bacillus sphaericus*) preserve their crystalline structure for three ethanol/water mixtures (20%, 40% and 60% ethanol). After exposing the S-layer surface to an ethanol/water mixture 80:20 (v/v), the 2-D crystalline structure was lost. Treatment with recrystallization buffer led to a recovering of the crystalline structure, showing that the S-layer surface can be denatured and renatured in a switched on-off process (see Figure 1). This fact could not be observed when the S-layer was exposed at different pH solutions and thermally treated. It was found that the 2-D crystalline structure was lost at pH 3 and at 55°C.

After studying the chemical and thermal stability of recrystallized S-layers on PEM, a novel hybrid sandwich-like supramolecular structure (polyelectrolyte/S-layer/polyelectrolyte/S-layer) was built. The supramolecular construct permitted to elucidate the bacterial affinity for different polyelectrolytes (Figure 2). It was found that only positive polyelectrolytes could adsorb on the exposed S-layer surface [7]. These results open a possibility to build functional hybrid supramolecular structures with potential applications in nanobiotechnology, and give insight about bacterial adhesion.

## References:

- [1] J. L. Toca-Herrera, R. Krastev, V. Bosio, S. Küpcü, D. Pum, A. Fery, M. Sara, U. B. Sleytr, *Small*, **1** (2005) 339.  
 [2] U. B. Sleytr, M. Sara, D. Pum, B. Schuster, *Progress in Surface Science*, **68** (2001) 231.  
 [3] D. Pum and U. B. Sleytr, *Landesr Academic Press*, Austin, TX, (1996) 175.  
 [4] B. Schuster and U. B. Sleytr, *Reviews in Molecular Biotechnology*, **74** (2000) 233.  
 [5] S. Küpcü, M. Sara, U. B. Sleytr, *Biochim. Biophys. Acta*, **1235** (1995) 263.  
 [6] D. Pum and U. B. Sleytr, *Thin Solid Films*, **244** (1994) 882.  
 [7] M. Delcea, R. Krastev, Th. Gutlebert, D. Pum, U. B. Sleytr, J. L. Toca-Herrera, *J. Nanosci. Nanotechnol.* In press.

## Figures:




Figure 1. Atomic force microscopy deflection images of S-layers recrystallized on PEM. a) S-layer just as it was formed; b) S-layer treated with EtOH/H<sub>2</sub>O 80/20 (v/v); c) Recovered S-layer after treatment with recrystallization buffer (S-layer protein renaturation).




Figure 2. Neutron reflectivity as a function of  $Q$  for the following macromolecular structures: 1- Si/PE/PSS-terminated, 2- Si/PE/PSS/S-layer, 3- Si/PE/PSS/S-layer/PAH, 4- Si/PE/PSS/S-layer/(PAH/PSS)<sub>2</sub> and 5-Si/PE/PSS/S-layer/(PAH/PSS)<sub>2</sub>/S-layer. Curves 2 and 3 show respectively the formation of the S-layer on PSS and the affinity of PAH to the S-layer. Note that curves 4 and 5 are similar, meaning that no homogenous S-layer was formed. PE=polyelectrolyte; PSS= Poly(sodium 4-styrenesulfonate); PAH= Poly(allylamine hydrochloride).